



Walnut Shell Powder 60/100

Specifications

Analysis

Specific Gravity:

pH Value at 25 °C (In Water):

Free Moisture (80 °C for 15 Hours):

Hardness – Vickers No.:

MOHS Scale:

Dry Packing Density (Pounds per Cubic Feet):

Nitrogen:

Cellulose:

Lignin:

Toluene Solubility:

Methoxyl:

Chlorine:

Ash:

Cutin:

Typical Results

1.2 – 1.5

4 – 6

3 – 9%

25 – 30

3 – 4

22 – 48

0.10

40/60

20/30

0.5/1.0

6.5

0.10

1.5

1.0

Screen:

US 60:

3.45%

US 80:

72.85%

US 100:

21.75%

Under US 100:

1.95%

Date: 03/03/2010

Disclaimer: All information, appearing herein on our products is based upon data that are believed to be reliable. However, it is the user's responsibility to determine the suitability of the product before use. Since the actual use of the product is beyond our control, no guarantee, express or implied, is made by Natural Sourcing of the product nor does Natural Sourcing assume any liability arising out of use, by others, of the product referred to herein.